Reply to Office Action of December 7, 2009

AMENDMENTS TO THE CLAIMS

1-10. (Cancelled)

11. (Currently Amended) A medical instrument comprising a medical instrument

substrate selected from the group consisting of a stent, a catheter and a medical tube, and a film

including a non-biodegradable resin and an amphiphilic substance, and having a porous structure

formed at least on its surface, the weight ratio of the amount of the non-biodegradable resin to

the amount of the amphiphilic substance being 99:1 to 50:50, the surface of the medical

instrument substrate being entirely or partially covered with the film, wherein the porous

structure of the film is a honeycomb structure, pores of the porous structure of the film have an

average pore size of 0.1 to 20 $\mu m,$ and the thickness of the film is 0.5 to 20 $\mu m.$

(Cancelled)

(Cancelled)

(Original) The medical instrument according to claim 11, wherein pores of the

porous structure of the film have a coefficient of variation in pore size of 30% or less.

15. (Original) The medical instrument according to claim 11, wherein the film is a

film or a stretched film obtained by casting a resin organic solvent solution onto a substrate,

2 MSW/VP

Application No. 10/580,648 Docket No.: 4252-0119PUS1
Amendment dated April 7, 2010

Reply to Office Action of December 7, 2009

causing the organic solvent to be evaporated and condensed on the surface of the cast solution,

and evaporating minute waterdrops produced by the condensation.

16-19. (Cancelled)

20. (Previously Presented) The medical instrument according to claim 11, wherein

the medical instrument substrate is a stent.

21. (Previously Presented) The medical instrument according to claim 20, which is a

digestive system stent.

22. (Previously Presented) The medical instrument according to claim 21, wherein

the digestive system stent is a bile duct stent.

23. (Previously Presented) The medical instrument according to claim 21, wherein

the digestive system stent is covered with a film including a resin and having a porous structure

formed by through-holes with an average pore size of 0.1 to 20 µm and a coefficient of variation

in pore size of 30% or less.

24-25. (Cancelled)

3 MSW/VP

Application No. 10/580,648 Amendment dated April 7, 2010 Reply to Office Action of December 7, 2009 Docket No.: 4252-0119PUS1

26. (New) The medical instrument according to claim 11, wherein the non-

biodegradable resin is 1,2-polybutadiene.

MSW/VP